

LOW-TEMPERATURE ELECTROWINNING FOR STEELMAKING (ULCOWIN)											
Date of factsheet	14-8-2020										
Author	Kira West										
Sector	Industry: Iron and steel										
ETS / Non-ETS	All										
Type of Technology	Emission reduction										
Description	<p>The electrowinning process, called ULCOWIN under the ULCOS project, is a low-temperature electrolysis process that produces solid state elemental iron from iron ore. Iron ore (or hematite, Fe2O3) particles are suspended in an alkaline electrolyte solution at about 100-110 °C. A current passes through the solution, from anode to cathode. Oxygen particles (with negative charge) are attracted to the anode, and are released at the surface of the solution, and elemental iron (with positive charge) forms crystals on the surface of the cathode. (Junjie 2018)</p> <p>The iron is then fed into an electric arc furnace (EAF) with a small amount of coke (or other carbon source for steelmaking) to make liquid crude steel. This iron can also be combined with scrap steel in the EAF, though this factsheet assumes that the iron input comes entirely from virgin iron from electrowinning. The EAF is a well-known, commercially mature technology that is widely used to produce mainly secondary steel using scrap and virgin materials. (European Commission 2016)</p>										
TRL level 2020	<p>TRL 5</p> <p>The electrowinning process has been demonstrated at pilot scale by both the ULCOS (Ultra-Low CO2 Steelmaking) and IERO (Iron production by electrochemical reduction of its oxide for high CO2 mitigation) projects. The Siderwin (Development of new methodologies for Industrial CO2-free steel production by electroWinning) project, running from 2017-2022, led by ArcelorMittal along with other industrial partners, with Horizon2020 funding, aims to bring the technology to TRL 6. (Siderwin 2019).</p>										
TECHNICAL DIMENSIONS											
Capacity	Functional Unit		Value and Range								
	Mton crude steel		-								
Potential			Current			2030			2050		
			-			-			-		
			Min	-	Max	Min	-	Max	Min	-	Max
Market share		%	-			-			-		
Capacity utilization factor			1.00								
Full-load running hours per year											
Unit of Activity	Mton crude steel/year										
Technical lifetime (years)											
Progress ratio											
Hourly profile	No										
Explanation	The current pilot plant has a capacity of only a few kilograms of output, and a pilot cell with about 100 kg capacity is under construction. (ArcelorMittal 2020) Because the technology has not yet been implemented at large scale, no potential or typical capacity has been estimated. However, the installation would be modular, with stacked electrolytic cells, and there is some experience with this type of technology in other metals sectors.										
COSTS											
Year of Euro	2015										
Investment costs	Euro per Functional Unit		Current			2030			2050		
	mIn. € / Mton crude steel		-			-			640.00		
Other costs per year			-			-			-		
			Min	-	Max	Min	-	Max	Min	-	Max
Fixed operational costs per year (excl. fuel costs)			-			-			45.00		
			Min	-	Max	Min	-	Max	45.00	-	45.00
Variable costs per year			-			-			-		
			Min	-	Max	Min	-	Max	Min	-	Max
Costs explanation	<p>CAPEX includes equipment needed for the full process from iron ore to crude steel. EAF CAPEX is included in these values. Fixed OPEX has not been described in the literature, and has therefore been estimated at about 7% of CAPEX, based on the fixed operating and maintenance cost for a small alkaline electrolyser cell for hydrogen production (Marsidi 2019). Variable costs (raw material costs, excluding energy costs) are around €199 million/Mton crude steel (European Commission 2016), including iron ore (1.51 t ore/t crude steel), limestone (0.143 t limestone/t crude steel), compressed air (64.8 normal cubic meters/t crude steel), and coke (0.03 t coke/t crude steel). European Commission (2016) does not break down variable costs in detail, but the largest share of variable costs are for iron ore purchase.</p> <p>European Commission (2016) provides annualized capital investment costs, without specifying a discount rate or equipment lifetime. The overnight capital costs from this source given in this factsheet were derived from the annualized costs assuming a range of discount rates of 5%-10% and equipment economic lifetimes of 10-20 years.</p>										
ENERGY IN- AND OUTPUTS											
Energy carriers (per unit of main output)	Energy carrier	Unit	Current			2030			2050		
	Main output: Electricity	PJ	-			-			11.96		
			Min	-	Max	Min	-	Max	11.34	-	14.26
	Natural gas	PJ	-			-			2.05		
			Min	-	Max	Min	-	Max	1.74	-	2.46
Coke		PJ	-			-			0.86		
			Min	-	Max	Min	-	Max	0.86	-	0.86
		PJ	-			-			-		
		Min	-	Max	Min	-	Max	Min	-	Max	
Energy in- and Outputs explanation	Natural gas is used for lime production, injected into the electric arc furnace as a supplemental heat source, and used in hot rolling. No natural gas is used for the electrowinning step.										
MATERIAL FLOWS (OPTIONAL)											
Material flows	Material	Unit	Current			2030			2050		
	Slag	Mton	-			-			-0.17		
			Min	-	Max	Min	-	Max	-0.17	-	-0.08
Crude steel		Mton	-			-			-1.00		
			Min	-	Max	Min	-	Max	-1.00	-	-1.00
Material flows explanation	Slag is produced in the electric arc furnace (EAF). Additional material flows are described below in the section "Other".										
EMISSIONS (Non-fuel/energy-related emissions or emissions reductions (e.g. CCS))											
Emissions	Substance	Unit	Current			2030			2050		
	CO2 (process)	Mton	-			-			-		
			Min	-	Max	Min	-	Max	-	-	-
	SO2	Mton	-			-			0.00		
			Min	-	Max	Min	-	Max	0.00	-	0.00
		Min	-	Max	Min	-	Max	Min	-	Max	
		Min	-	Max	Min	-	Max	Min	-	Max	
Emissions explanation	The only direct CO2 emissions from electrowinning steelmaking are from potential natural gas use for the EAF and hot rolling steps. No process CO2 is emitted; O2 is produced from the electrolytic cell. Oxygen has not been considered as an "emission" as it could be captured and sold or utilized.										

OTHER										
Parameter	Unit	Current			2030			2050		
		Min	-	Max	Min	-	Max	Min	-	Max
Oxygen	million Nm ³	-	-	-	-	-	-	-260.00	-	-260.00
Iron ore	Mton	-	-	-	-	-	-	1.51	-	1.51
		Min	-	Max	Min	-	Max	1.51	-	1.51
Limestone	Mton	-	-	-	-	-	-	0.03	-	0.14
		Min	-	Max	Min	-	Max	0.03	-	0.14
Compressed air	million Nm ³	-	-	-	-	-	-	64.80	-	64.80
		Min	-	Max	Min	-	Max	64.80	-	64.80
Explanation	Oxygen is a byproduct of the electrolytic process, and is given in units of million normal cubic meters. The coke, though it has energy content, is injected into the EAF as a raw material to provide a carbon source for the steel and is not combusted.									
REFERENCES AND SOURCES										
European Commission (2016), "Iron production by electrochemical reduction of its oxide for high CO2 mitigation" (IERO), https://publications.europa.eu/en/publication-detail/-/publication/4255cd56-9a96-11e6-9bca-01aa75ed71a1 .										
Yan Junjie (2018), "Progress and Future of Breakthrough Low-carbon Steelmaking Technology (ULCOS) of EU", http://www.sciencepublishinggroup.com/journal/paperinfo?journalid=371&doi=10.11648/j.ijmpem.20180302.11 .										
Jean-Pierre Birat (2011), "Update on the ULCOS program," http://erc-online.eu/wp-content/uploads/2014/04/2011-00612-E.pdf .										
Rainer Remus, Miguel A. Aguado-Monsonet, Serge Roudier, and Luis Delgado Sancho (2013), "Best Available Techniques (BAT) Reference Document for Iron and Steel Production," https://eippcb.jrc.ec.europa.eu/reference/i&s.html .										
Pasquale Cavaliere (2019), Clean Ironmaking and Steelmaking Processes: Efficient Technologies for Greenhouse Emissions Abatement. Springer: Lecce, Italy.										
World Steel (2019), "Steel Statistical Yearbook 2019 Concise version", downloaded from: https://www.worldsteel.org/en/dam/jcr:7aa2a95d-448d-4c56-b62b-b2457f067cd9/SSY19%2520concise%2520version.pdf .										
Siderwin (2019), "Development of new methodologies for Industrial CO2-free steel production by electroWinning," https://www.siderwin-spire.eu/content/home .										
Boston Consulting Group (2013), "Steel's Contribution to a Low-Carbon Europe 2050," https://www.bcg.com/publications/2013/metals-mining-environment-steels-contribution-low-carbon-europe-2050.aspx .										
Institute for European Studies (2018), "Annex: Technology Database," https://www.ies.be/files/ANNEX_Technology_Database_13072018.pdf .										
Fischedick, M. et al (2014), "Techno-economic evaluation of innovative steel production technologies," Journal of Cleaner Production, pp 563-580.										
Abdul Quader, M. et al. (2016), "Present needs, recent progress and future trends of energy-efficient Ultra-Low Carbon Dioxide (CO2) Steelmaking (ULCOS) program," Renewable and Sustainable Energy Reviews, Vol. 55, pp. 537-549.										
Arcelor Mittal (2020), "Siderwin, targeting radically new steel production without CO2 emissions", https://automotive.arcelormittal.com/news_and_stories/news/2019Siderwin .										
Netherlands Enterprise Agency (RVO) (2019), "The Netherlands: list of fuels and standard CO2 emission factors: version of January 2019", https://english.rvo.nl/sites/default/files/2019/05/The%20Netherlands%20list%20of%20fuels%20version%20January%202019.pdf .										
A. Keys, M. van Hout, and B. Daniëls (2019), "Decarbonisation Options for the Dutch Steel Industry," MIDDEN report, https://www.pbl.nl/sites/default/files/downloads/pbl-2019-decarbonisation-options-for-the-dutch-steel-industry_3723.pdf .										
Marsidi, M. (2019), "Alkaline-electrolysis hydrogen installation - small scale," https://energy.nl/en/fact_sheet/small-scale-alkaline-electrolysis-h2-installation/ .										